

Date of Issue: August 2015

Affected Publication: API Specification 20A, *Carbon Steel, Alloy Steel, Stainless Steel, and Nickel Base Alloy Castings for Use in the Petroleum and Natural Gas Industry*, First Edition, March 2012

ERRATA 1

Page 21, Table 10 shall be replaced with the following:

Table 10—Wall Thickness up to 2 inches, in Accordance with ASTM E446

Discontinuity Type	Category	Acceptable Comparative Plate	
		CSL-2 and CSL-3	CSL-4
Gas	A	A3	A2
Sand	B	B3	B2
Shrinkage, Type 1	C	CA2	2 (All types)
Shrinkage, Type 2	C	CB3	2 (All types)
Shrinkage, Type 3	C	CC3	2 (All types)
Shrinkage, Type 4	C	CD3	2 (All types)
Hot tears and cracks	D and E	None	None
Inserts (internal chills & metal chaplets)	F	None	None