

Date of Issue: September 2018

Affected Publication: API Specification 20E, *Alloy and Carbon Steel Bolting for use in the Petroleum and Natural Gas Industries*, Second Edition, February 2017

Addendum 1

Page 1: The following note shall be placed after clause 1.4:

NOTE Alternate geometry components made in accordance with this specification may be specified by the purchaser.

Page 13: The second sentence of clause 5.7.1 shall be replaced with the following:

When heat treated without interruption in continuous furnaces, as defined in 3.1.5, testing shall be as follows: Not fewer than two tests for the first 20,000 lb. (9000 kg) or less, and an additional test for every 10,000 lb. (4500 kg) or fraction thereof.