

API Specification

National Adoption of ISO 3183:2007—Petroleum and natural gas industries—Steel pipe for pipeline transportation systems

5L

45th Edition, December 2012

Specification for Line Pipe

The following information is contained in Section 7 of API Specification 5L, 45th Edition

7 Information to be supplied by the purchaser

7.1 General information

The purchase order shall include the following information:

- a) quantity (e.g. total mass or total length of pipe);
- b) PSL (1 or 2);
- c) type of pipe (see Table 2);
- d) reference to API 5L;
- e) steel grade (see 6.1, H.4.1.1, or J.4.1.1, whichever is applicable);
- f) outside diameter and wall thickness (see 9.11.1.2);
- g) length and type of length (random or approximate) (see 9.11.1.3, 9.11.3.3 and Table 12);
- h) confirmation of applicability of individual annexes.

7.2 Additional information

The purchase order shall indicate which of the following provisions apply for the specific order item:

- a) Items that are subject to mandatory agreement, if applicable:
 - 1) pipe designation for intermediate grades [see Table 1, footnote a)],
 - 2) chemical composition for intermediate grades (see 9.2.1 and 9.2.2),
 - 3) chemical composition for pipe with $t > 25,0$ mm (0.984 in) (see 9.2.3),
 - 4) carbon equivalent limits for PSL 2 pipe in Grade L415N or X60N (see Table 5),
 - 5) carbon equivalent limits for PSL 2 pipe in Grade L555Q or X80Q, L625Q or X90Q, and L690Q or X100Q (see Table 5),
 - 6) carbon equivalent limits for PSL 2 SMLS pipe with $t > 20,0$ mm (0.787 in) [see Table 5, footnote a)],
 - 7) diameter and out-of-roundness tolerances for pipe with $D > 1\,422$ mm (56.000 in) (see Table 10),
 - 8) diameter and out-of-roundness tolerances for the ends of SMLS pipe with $t > 25,0$ mm (0.984 in) [see Table 10, footnote b)],
 - 9) standard applicable to jointer welds (see A.1.2);
- b) Items that apply as prescribed, unless otherwise agreed:

API Specification

5L

45th Edition, December 2012

Specification for Line Pipe

- 1) range of sizing ratio for cold-expanded pipe (see 8.9.2),
 - 2) equation for sizing ratio (see 8.9.3),
 - 3) chemical composition limits for PSL 1 pipe [see Table 4, footnotes c), e) and f)],
 - 4) chemical composition limits for PSL 2 pipe [see Table 5, footnotes c), e), f), g), h), i), k), and l)],
 - 5) yield/tensile ratio for grades L625Q or X90Q, L690 or X100 and L830 or X120 [see Table 7, footnotes g and h or Table J.2, footnotes h and i],
 - 6) estimation and reporting of Charpy shear area (see 9.8.2.3),
 - 7) tolerances for random length pipe [see 9.11.3.3 a)],
 - 8) type of thread compound (see 9.12.2.4),
 - 9) type of end face (see 9.12.5.1 or 9.12.5.2),
 - 10) International Standard applicable to Charpy testing (see 10.2.3.3, 10.2.4.3, D.2.3.4.2 and D.2.3.4.3),
 - 11) product analysis method (see 10.2.4.1),
 - 12) alternate method for diameter measurement for $D \geq 508$ mm (20.000 in) (see 10.2.8.1),
 - 13) jointer welding type (see A.1.1),
 - 14) offset of longitudinal pipe weld seams at jointer welds (see A.2.4),
 - 15) repairs in cold-expanded pipe (see C.4.2),
 - 16) alternate IQI type (see E.4.3.1);
- c) Items that apply, if agreed:
- 1) delivery condition (see 6.2 and Table 1),
 - 2) supply of quenched and tempered PSL 1 Grade L245 or B SMLS pipe (see Table 1),
 - 3) supply of intermediate grades [see Table 2, footnote a)],
 - 4) supply of double-seam SAWL pipe [see Table 2, footnote c)],
 - 5) alternative to specified seam heat treatment for PSL 1 pipe (see 8.8.1),
 - 6) supply of SAWH pipe with coil/plate end welds at the pipe ends (see 8.10.3),
 - 7) supply of jointers (see 8.11),
 - 8) CVN impact test temperature lower than 0 °C (32 °F) (see 9.8.2.1, 9.8.2.2 and 9.8.3),
 - 9) CVN impact test of the pipe body of PSL 2 welded pipe with $D < 508$ mm (20.000 in) for shear fracture area (see 9.8.2.2 and Table 18),
 - 10) CVN impact test of the longitudinal seam weld of PSL 2 HFW pipe (see 9.8.3 and Table 18),

API Specification

5L

45th Edition, December 2012

Specification for Line Pipe

- 11) DWT test of the pipe body of PSL 2 welded pipe with $D \geq 508$ mm (20.000 in) (see 9.9.1 and Table 18),
- 12) DWT test temperature lower than 0 °C (32 °F) (see 9.9.1),
- 13) fraction jointers comprising 2 or 3 pieces for 12 m (40 ft) nominal or 24 m (80 ft) nominal, respectively [see 9.11.3.3.c), d), and e)],
- 14) power-tight make-up of couplings (see 9.12.2.3 and 10.2.6.1),
- 15) special bevel configuration (see 9.12.5.3),
- 16) removal of outside weld bead at pipe ends of SAW or COW pipe [see 9.13.2.2 e)],
- 17) weldability data or tests for PSL 2 pipe (see 9.15),
- 18) type of inspection document for PSL 1 pipe (see 10.1.2.1),
- 19) manufacturing information for PSL 1 pipe (see 10.1.2.2),
- 20) alternative type of inspection document for PSL 2 pipe (see 10.1.3.1),
- 21) use of transverse test pieces for tensile tests of SMLS pipe, not cold-expanded [see Table 20, footnote c)],
- 22) use of the ring expansion test for transverse yield strength determinations [see 10.2.3.2, Table 19 note c), and Table 20 note d)],
- 23) use of an alternative to macrographic examination (see 10.2.5.2),
- 24) hardness test during production of EW and LW pipe (see 10.2.5.3),
- 25) specific condition to be used for hydrostatic tests for threaded and coupled pipe (see 10.2.6.1),
- 26) alternate hydrotest pressure (see Table 26),
- 27) use of minimum permissible wall thickness to determine hydrostatic test pressure (see 10.2.6.7),
- 28) specific method to be used for determining pipe diameter (see 10.2.8.1),
- 29) use of inside diameter measurements to determine diameter and out-of-roundness for expanded pipe with $D \geq 219,1$ mm (8.625 in) and for non-expanded pipe [see 10.2.8.3 and Table 10, footnote c)],
- 30) specific method to be used for determining other pipe dimensions (see 10.2.8.7),
- 31) paint-stencilled markings for couplings (see 11.1.2),
- 32) additional markings specified by the purchaser (see 11.1.4),
- 33) specific surface or location for pipe markings [see 11.2.2 b) and 11.2.6 b)],

API Specification

5L

45th Edition, December 2012

Specification for Line Pipe

- 34) die-stamping or vibro-etching of pipe (see 11.2.3),
- 35) alternative location for marking the pipe (see 11.2.4),
- 36) alternative format for pipe length marking locations (see 11.2.6 a),
- 37) colour identification for pipe (see 11.2.7),
- 38) multiple grade marking (see 11.4.1),
- 39) temporary external coating (see 12.1.2),
- 40) special coating (see 12.1.3),
- 41) lining (see 12.1.4),
- 42) manufacturing procedure qualification for PSL 2 pipe, in which case Annex B shall apply (see B.2),
- 43) radiographic inspection of SAW seam or coil/plate end weld (see Table E.1),
- 44) non-destructive inspection of PSL 1 SMLS pipe (see E.3.1.2),
- 45) NDT of EW seam welds after hydrotest [see E.3.1.3 b)],
- 46) ultrasonic inspection of welded pipe for laminar imperfections at pipe ends (see E.3.2.3),
- 47) ultrasonic inspection of SMLS pipe for laminar imperfections at pipe ends (see E.3.3.2),
- 48) radiographic inspection in accordance with Clause E.4,
- 49) use of both holes and notches in ultrasonic reference standard (see Table E.7),
- 50) alternative re-inspection technique for COW seams (see E.5.5.5),
- 51) ultrasonic inspection for laminar imperfections in the pipe body of EW, SAW or COW pipe (see E.8),
- 52) ultrasonic inspection for laminar imperfections along the coil/plate edges or the weld seam of EW, SAW or COW pipe (see E.9),
- 53) supply of welded couplings on pipe with $D \geq 355,6$ mm (14.000 in) (see F.1.4),
- 54) application of Annex G to PSL 2 pipe where purchaser shall specify the toughness test temperature, the minimum energy for each test and the minimum average energy value required for the order (see G.2),
- 55) PSL 2 pipe for sour service, in which case, Annex H shall apply (see H.2),
- 56) TFL pipe, in which case Annex I shall apply (see I.2),
- 57) pipe for offshore service, in which case Annex J shall apply (see J.2),
- 58) any other additional or more stringent requirements.